

Material Test Report

Report Number: 676744.00-5
Issue Number: 2 - This version supersedes all previous issues
Reissue Reason: 3.35mm sieve added
Date Issued: 20/06/2023
Client: Austone Pty Ltd
 131 Barnetts Road, Macksville NSW 2447
Contact: David Beams
Project Number: 676744.00
Project Name: Material Testing
Project Location: 131 Barnetts rd, Gumma NSW
Work Request: 17959
Sample Number: CF-17959A
Date Sampled: 30/05/2023
Dates Tested: 30/05/2023 - 20/06/2023
Sampling Method: AS 1141.3.1 8.4.3 - Sampling from the sides of the stockpile
Preparation Method: AS 1289.1.1 - Sampling and preparation of soils
Sample Location: E: 6604014, N: 498019
Material: 6mm Pebble
Material Source: Gumma Quarry



Accredited for compliance with ISO/IEC 17025 - Testing

Approved Signatory: Brandon Cameron
 Assistant Laboratory Manager
 Laboratory Accreditation Number: 828

| Particle Size Distribution (AS1141.11.1) | | |
|--|-----------------------|----------------|
| Sample Washing | Sample was not washed | |
| Sieve | Passed % | Passing Limits |
| 6.7 mm | 100 | |
| 4.75 mm | 91 | |
| 3.35 mm | 51 | |
| 2.36 mm | 13 | |
| 1.18 mm | 1 | |

